



DE4114518

Biblio

Desc

Claims

Page 1

Drawing

esp@cenet



No title available.

Patent Number: DE4114518

Publication date: 1992-11-05

Inventor(s): LITZKE DIETER (DE); KAHRMANN PHILIPP (DE)

Applicant(s): LS INDUSTRIELACKE GMBH (DE)

Requested

Patent: ☒ DE4114518

Application

Number: DE19914114518 19910503

Priority Number

(s): DE19914114518 19910503

IPC

Classification: B05C1/08 ; B05C9/14 ; B05C21/00 ; B05D1/38 ; B05D3/06 ; B05D3/10 ; B05D3/14 ; B05D7/08 ; C09D7/02 ; C09D7/06 ; C09D7/12 ; C09D161/20

EC

Classification: C09D161/20

Equivalents:

Abstract

A surface coating material (I) is claimed, for the prodn. of hard, resistant base coat and/or top coat surfaces on wood, timber prods. etc.; (I) contains a water-thinnable, low-anti-settling additive, opt. a pigment and plasticiser, and a catalyst adduct (II) consisting of an organic acid (IIA) and a melamine resin (IIB). Pref. (IIA) is mono-butylphosphonic acid, maleic acid or p-toluenesulphonic acid, and (IIB) contains up to 80 wt.% solids. (II) contains (for textured surfaces) 60 wt.% (IIA), 10 wt.% (IIB) and 30 wt.% water or (for smooth surfaces) 60 wt.% (IIA), 10 wt.% (IIB), 4 wt.% silicic acid and 26 wt.% water. Basecoat compsn. contains 70 wt.% liq, formaldehyde resin, 15 wt.% liq, melamine resin, 10 wt.% kaolin, 1 wt.% anti-settling agent, 0.2 wt.% levelling soln., and 3.8 wt.% water, or 50 wt.% UF resin, 15 wt.% melamine resin, 18 wt.% kaolin, 15 wt.% TiO₂, 0.2 wt.% levelling soln. and 1.8 wt.% water. Topcoat compsn. contains 75 wt.% UF resin, 15 wt.% melamine resin, 3 wt.% plasticiser, 5 wt.% wax dispersion, 0.2 wt.% levelling soln. and 1.8 wt.% water, or 60 wt.% formaldehyde resin, 15 wt.% melamine resin, 3 wt.% plasticiser, 5 wt.% wax dispersion, 15 wt.% TiO₂, 0.2 wt.% fatty alcohol sulphonate and 1.8 wt.% water.

Data supplied from the esp@cenet database - I2